



Storm Greeter™ Pre-Cured Coating Product Data Sheet

DESCRIPTION:

Storm Greeter Pre-Cured coating is a dispersion of PVC resin in liquid plasticizer, cured to an inert state.

PRODUCT BENEFITS:

- Cushioning
- UV Resistance
- Sound Dampening
- Corrosion Resistance
- Electric Insulation
- Multiple Colors

Passed the 14,000 and 23,000 volt thresholds in both *phase to ground* and *phase to phase* applications at **Florida Power & Light's Reliability Assurance Center**

PHYSICAL CHARACTERISTICS:

| | |
|------------------------------|----------------------------------|
| Hardness (Shore A) D2240 | 75 (+/-5) |
| Tensile (PSI) D412 | 2,000 (+/-200) |
| Elongation (%) D412 | 350 (+/-50) |
| Tear Strength (PPI) D412 | 280 (+/-28) |
| Low Service Temp. --- F (C) | ---22 (---30) |
| High Service Temp. --- F (C) | 225 (107) |
| Dielectric Strength (v/ml) | 400 v/mil thickness, min. 3 mils |

SAFETY:

This product contains no Volatile Organic Compounds (VOC). See Material Safety Data Sheet (MSDS) for more safety information

LIMITATIONS:

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Any liability we may have with respect to a product or its use (including liability for breach of warranty, strict liability in tort, negligence or otherwise) is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental and consequential damages.